

TEST REPORT**APPLICANT:**

Quanzhou Licheng Jiayi Plastics Products
 Factory
 No.20, Shangfu Wang Gong Fugiao, Licheng,
 Quanzhou

REPORT NUMBER: WOSZ47593 (A)**DATE:** May 8 2012**Attn:** Hu Song Xu**SAMPLE DESCRIPTION:**

One(1)submitted sample said to be Sport Absorbs Water Bag with four tested components:

- (1) Semi-Transparent blue Plastic(body of bag)
- (2) blue plastic(lid)
- (3)Semi-transparent blue Plastic(body of lid)
- (4)Transparent Plastic(pipe)

Ref.No:SHB

Country of origin:

China

Sample received date:

May 5, 2012

Date of testing started:

May 5, 2012

Date of testing ended:

May 6, 2012

TEST CONDUCTED:**AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGE(S)****CONCLUSION:**

Tested Samples	Standard	Result
Tested components of submitted sample	European Standard on Safety of Toys EN71 Part 3 : 1994 with Amendment A1 : 2000 -Toxic Elements Analysis	Pass

PAGE 1/TO BE CONTINUED

TOTAL 2 PAGES

AUTHORIZED BY:
INTERTEK TESTING SERVICES
SHENZHEN LTD.




JOHN QIN
GENERAL MANAGER (RAM DIVISION)

TEST REPORT

REPORT NUMBER: WOSZ47593 (A)

TEST CONDUCTED:

Toxic Elements Analysis

As per European Standard on Safety of Toys EN71 Part 3: 1994 with Amendment A1:2000, acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma Spectrometry.

Element	Limit	Result (mg/kg)			
		(1)	(2)	(3)	(4)
Soluble Lead	90 mg/kg	<2	<2	<2	<2
Soluble Barium	1000 mg/kg	<2	<2	<2	<2
Soluble Cadmium	75 mg/kg	<2	<2	<2	<2
Soluble Arsenic	25 mg/kg	<2	<2	<2	<2
Soluble Mercury	60 mg/kg	<2	<2	<2	<2
Soluble Chromium	60 mg/kg	<2	<2	<2	<2
Soluble Selenium	500 mg/kg	<2	<2	<2	<2
Soluble Antimony	60 mg/kg	<2	<2	<2	<2

mg/kg = milligram per kilogram based on dry weight of wet paint

< = less than

The analysis results were adjusted by subtracting analytical correction factor.

PAGE 2 OF 2 PAGES

END OF REPORT